



## Træarters densitet

Dansk	Latin	Densitet ved 12% fugt, kg/m <sup>3</sup>
Abachi	Triplochiton scleroxylon	390
Ahorn/Ær	Acer spp.	560
Ask	Fraxinus spp.	690
Azobé	Lophira alata	1050
Balsa	Ochroma lagopus	150
Bilinga	Nauclea spec. div.	900
Bintangor	Calophyllum spp.	660
Birk	Betula spp.	650
Bøg	Fagus sylvatica	680
Canga	Aspidosperma spp.	900
Cumaru	Dypteryx odorata	1050
Denya	Cylicodiscus gabunensis	920
Douglas	Pseudotsuga menziesii	530
Doussié	Azelia bipindensis	785
Europæisk eg	Quercus spp.	680
Europæisk Lærk	Larix decidua	550
Fuglekirsebær	Prunus avium	600
Greenheart	Chlorocardium rodiei	1000
Guariuba	Clarisia racemosa	630
Ipé	Handroanthus spec. div.	1050
Iroko	Milicia excelsa, M. regia	660
Jatoba	Hymenaea spp.	900
Karri	Eucalyptus diversicolor	850
Keruing	Dipterocarpus spp.	800
Khaya Mahogni	Khaya grandifolia	575
Krydsfiner	Krydsfiner	550
Limba	Terminalia superba	560
Massaranduba	Manilkara bidentata	950
Meranti	Shorea spp.	675
Merbau	Intsia buijuga	800
OSB	OSB	600
Pil	Salix viminalis	450
Poppel/asp	Populus spp.	440
Radiata Fyr	Pinus radiata - Accoya	510
Redwood	Sequoia sempervirens	380
Robinie	Robinia pseudoacacia	750
Rødgran	Picea spp.	400
Sapele Mahogni	Entandrophragma cylindricum	650

Sipo Mahogni	Entandrophragma utile	640
Skovfyr	Pinus sylvestris	510
Spånplade	Spånplade	650
Tali	Erythrophleum spec. div.	900
Teak	Tectona grandis	675
Thuja	Thuja plicata	360
Valnød	Juglans spp.	550
Wengé	Millettia laurentii	875
Ædelgran	Abies spp.	420
Ægte Kastanje	Castanea sativa	550